

TECHNICAL DATA SHEET

HEAVY DUTY VARNISH INTERIOR POLYURETHANE

DESCRIPTION

Polyvine Interior Heavy Duty Varnish is composed of a water-based dispersion of cross-linking polyurethane copolymer with surfactants, waxes, and rheology modifying agents.

An ultra hard, high-quality varnish that dries to a crystal-clear film for interior surfaces requiring a high level of protection such as working surfaces and areas of high wear. This product is self-extinguishing.

Polyvine Heavy Duty Varnish is ideal for use on wood surfaces; emulsion paint, tables, bookshelves, chairs, desks, kitchen cabinets, work surfaces, to give an extremely hard clear protective coating with a high degree of heat, water, chemical and abrasion resistance.

Dries to a finish, which is capable of withstanding heavy wear and abrasion after 16 hours curing.

FOR USE ON

Internal wood • doors • wooden worktops • tabletops • furniture • kitchen cabinets • shelving • wood panelling and other surfaces, in such areas as Homes, Hotels, Shop fitting, Restaurants and Bars.

For floors use: Polyvine Heavy Duty Floor Varnish

AVAILABLE FINISHES

Satin for depth and a soft sheen, dead flat for a completely shine free surface.

UNIQUE SELLING POINTS

Highly chemical resistant, cures in 16 hours, very fast drying and recoating, highly stain resistant, water resistant, highly heat resistant, industrial level of finish.

SURFACE PREPARATION

All surfaces must be clean and free from dust, dirt, oil/resins and contamination.

APPLICATION

Ensure the product is well mixed but do not shake (inverting the container several times allows the particles to distribute evenly throughout the varnish) creating a uniform solution.

Ensure the surface to be coated is clean and free from grease, wax or polish. If water has been used on bare wood this would raise the grain. The surface then needs to be sanded and vacuumed before coating.

Use a Polyvine varnish synthetic brush, recommended, or by conventional spray or HVLP spray or Gloss Roller. Roller, take care, stippling may occur, do not apply pressure this will generate air bubbles in the varnish.

Thinly apply 2 to 3 coats with a Polyvine brush. On porous surfaces dilute the first coat with 10% water.

For a dead flat finish with high durability (water, stain, abrasion, resistance), apply two coats of satin followed by one of dead flat.

As with all water-based coatings, do not apply at temperatures below 8°C (as recommended by British Standard BS 6150). Or above 30°C.

TECHNICAL DATA SHEET

CAUTION

Apply dead flat finish sparingly and brush out well, over application could result in misting. Always apply to a test area before starting work. Care must be taken when applying in high temperature or direct sunlight as this will affect drying time. Do not continuously submerge in water. Test for compatibility before application. Not suitable for exterior application.

Spills should be promptly removed. Unattended spills may cause cosmetic staining and potentially damage the surface.

Plasticisers found in materials such as carpet underlays, furniture legs, castors and adhesives used for fixing can lead to softening and discolouration.

Appearance may vary according to the colour and type of substrate and the number of coats.

COVERAGE

Coverage 15-20 sq. m per litre, 160-215 sq. ft per quart depending on the porosity of the substrate.

NUMBER OF COATS

See application section.

Cure Time: Up to 5 days @ 20°C / 70°F

Drying Time: 45 minutes

Recoat Time: 2 hours

PACKAGING

100ml, 500ml, 1L, 4L, 3.52oz, US pint, US Quart, US gal. plastic containers.

STORAGE

Protect from extremes of temperature during storage and application.

Store in unopened containers in a cool dry place away from direct sunlight.

Shelf Life: Many years in tightly sealed container.

HEALTH SAFETY AND THE ENVIRONMENT

Non-hazardous Keep out of reach of children. Contact with eyes - wash immediately with warm water.

If swallowed, seek medical advice immediately and show the container or label.

Do not empty into drains, dispose of this material and its container at hazardous or special waste collection point.

CLEAN UP EQUIPMENT

Any equipment used can be cleaned using soap and water before the clear coat dries. Wipe any excess off surfaces with a damp cloth. Any dried deposits will need Polyvine Varnish and Paint Remover to remove them.

TECHNICAL DATA SHEET

DISPOSAL

Look for special facilities locally. Do not empty into drains or watercourses.

The information provided is prepared to the best of our current knowledge and makes no claim to be complete. The User is responsible for establishing that the product and recommendations herein are fit for the designated purpose, wood type and present situation before use. A professional and thereby successful application of the product is beyond our control. Always make a preliminary test. The User is required to read and understand all information contained on package labels and safety data sheets before using this product.

Certifications: EN codes and standards

Eco Credentials

EN 13501-1; Reaction to fire Self-Extinguishing

EN 71-3: Application on children's toys

EN. 1935/2004 on materials and articles intended to come into contact with food. Food Safety

EN 71-3:2019 + A1:2021 Pet Safety

MANUFACTURED IN THE UK BY

TEL 01934 740305 **EMAIL** info@polyvine.co.uk

For technical and recycling info visit our website **polyvine.com**

EU VOC limit 130g/L 2010 (cat A/e) contains 44g/L

DATE OF ISSUE PW final 10.24 04/12/2024