

## CASCAMITE WBP

### DESCRIPTION

Cascamite WBP Unique synthetic resin wood glue, water and boil proof, withstands continual immersion in water, gap filling and structural. Ensures completely waterproof joints in all temperatures. Ideal for all exterior woodwork and joinery subject to prolonged water exposure. It attains bond strength very fast, enabling it to be used for load bearing and laminating. Use where high bond strength, gap filling and complete waterproofing is required.

### AREAS OF USE

exterior joinery • ships • boats • jetties and marinas • windows and doors • gates • garden furniture • shop fitting • kitchens • worktops • bathrooms • veneering • laminating

### ADVANTAGES

Simple mix with water  
Structural  
Gap Filling  
Water and Boil proof  
Interior or Exterior Use  
Easy to Mix  
Non-Staining  
Mould Resistant  
Stronger Bond Than The Wood Itself

**tack time:** 5 hours at 10°C, 2 hours at 20°C, 1 hour at 30°C cure time: check remainder of mixed glue, cured when hard

### MIXING

By Weight.  
Use 2 parts of Cascamite powder to 1 part of cold water.  
By Volume  
NOTE: Mixing by weight is recommended for accurate and consistent glue mixes.

Add Cascamite powder to water, stirring rapidly until the powder dissolves.  
Any small lumps will quickly dissolve.  
Up to 20% extra water can be added to improve flow.  
It is advisable to allow the mixture to stand after mixing to allow entrapped air to escape, bubbles or foam in a glue line can cause a weak bond. Cascamite is now ready for use. The mixture will remain usable for approx. 3 hours at 15°C

At higher temperatures the usable life is reduced and in hot weather it is advisable to mix only sufficient glue for immediate use (standing the mixing vessel in cold water will help prevent shortening of the usable life).

**tack time:** 3 hours at 10°C, 45 minutes at 20°C, 20 mins at 30°C cure time: Keep and check remainder of mixed glue, cured when hard

It is advisable to allow the mixture to stand after mixing to allow entrapped air to escape, bubbles or foam in a glue line can cause a weak bond. Cascamite WBP is now ready for use.  
The mixture will remain usable for approx. 3 hours at 15°C

At higher temperatures the usable life is reduced and in hot weather it is advisable to mix only sufficient glue for immediate use (standing the mixing vessel in cold water will help prevent shortening of the usable life).

### APPLICATION

Joints should be smooth and well fitted. Apply the glue using a stiff brush to one surface only.  
Assemble and clamp (pin or screw) the joint whilst glue is wet.  
Keep the joint under pressure until set (approx. 6 hours at 15°C)  
A damp cloth can be used to remove excess wet adhesive.

Further information may be obtained from:

Polyvine Limited, Vine House, Cheddar Business Park, Wedmore Road, Cheddar, BS27 3EB

Tel 01934 740305 • [www.polyvine.com](http://www.polyvine.com) • email [info@polyvine.co.uk](mailto:info@polyvine.co.uk)

NOTE: - At temperatures below 10C (50F), a period of up to 2 or 3 days may be required before the glue sets. During cold weather, it is therefore essential that joints under pressure be kept in a warm place.

Coverage should be 100 to 250 grams/sq. metre

**NOTE:** - If bonded wood is to be turned on a lathe it is recommended that the bonded wood is seasoned for a minimum of one week before turning.

## **USE OF PRESS ON ADHESIVE**

The press pressure influences penetration of adhesives because it is the driving force for hydrodynamic flow. The pressure applied on the adhesive will force it to spread and penetrate into porous, fibrous material and into the roughness of the surfaces. The bond quality is affected by the amount of adhesive penetration into wood substrate during manufacture. An optimum adhesive penetration is needed to provide a reliable glue line thickness (GLT).

The press pressure is one of the main factors to control the GLT in addition to adherent, adhesive, machining, and adhesive spreading. GLT should be controlled because it directly affects the strength of bonding. One of the most important reasons for the occurrence of a thick glue line is insufficient pressure in the gluing process. Generally, thick glue lines lack strength. Pressure must be applied uniformly and adequately because synthetic resin based structural wood adhesives are not able to form strong bonds in thick and variable thickness glue lines.

The GLT's for wood joints are generally between 0.127 and 0.178mm. Optimum press pressures should be determined in relation to GLT. In low-density woods, high pressure forces the adhesive so deeply into the wood that there is insufficient adhesive to fill the bond-line, and it may cause over-penetration and inferior bond strength. On the other hand, low pressure causes a decrease in shear strength, does not provide close contact between the surfaces, and glue line remains partly poor.

The optimum press pressure was found to be  $12.5\text{kg cm}^{-2}$ . It may be risky to use pressure higher than  $12.5\text{kg cm}^{-2}$  or lower than  $7.5\text{kg cm}^{-2}$  at this level of spreading rate and heat with the UF adhesive because of possible bonding and joint starvation problems, respectively.

The press pressure may depend on wood species, the moisture content of wood, adhesive properties, other press parameters, factory conditions, and strength requirements.

We recommend tests be conducted to establish the customers optimum press pressures.

## **BONDING TIPS**

1 Ideally the moisture content of the substrates should be  $9\% \pm 2\%$  with no more than 3% difference between the two surfaces to be bonded, otherwise stresses are built into the joint, which may result in wood or joint fracture. If the wood is too damp, the dilution effect will weaken the adhesive performance.

2. Although the workshop conditions may be above 10C, wood brought in from unheated storage conditions may well be below this temperature and should be allowed to warm to above 10C before attempting to bond it.

3. Some species of oak can be particularly dense resulting in difficulties in the adhesive penetrating the surface. In such instances, the surface should be removed by sanding to open the pores of the timber and double spreading may prove necessary to ensure both surfaces have sufficiently "wetted" out.

4. Some timbers, and particularly maple can be over prepared by planeing the timber; this leaves a "glassy" surface, which is detrimental to the bonding process.

5. Oily timbers, such as teak, present problems with the "oils" inhibiting a satisfactory bond. Degreasing is normally required; this can be achieved by wiping the surface with methylated spirit. Sanding can also remove surface grease, but if the adhesive is not applied shortly afterwards there are likely to be problems of case hardening where the oils have surfaced again.

Timber bought as kiln dried and stored under cover will present no problem.

Perhaps as important as the glue is the preparation the joining surfaces, especially for Oak and oily

Further information may be obtained from:

Polyvine Limited, Vine House, Cheddar Business Park, Wedmore Road, Cheddar, BS27 3EB

Tel 01934 740305 • [www.polyvine.com](http://www.polyvine.com) • email [info@polyvine.co.uk](mailto:info@polyvine.co.uk)

timbers, Teak, Iroko etc.

Timber direct from machining has a slightly glazed surface and the surface fibres are compressed by rollers etc, far from ideal and it is essential that the surfaces to be joined should be ridded of this unwanted smoothness.

Use a scouring plane (blade with fine points), hacksaw blade, or very coarse sandpaper. Plywood must be, treated in the same manner. Dust with a bristle brush, oily timbers should be degreased with methylated spirit. The faying area should be abraded as close to bonding as practically possible. As important as preparation, is working in the correct temperature and that means, within reason, as warm as possible, 20C is ideal. At higher temperatures the glue becomes much less viscous, easier to apply and penetrates the timber instead of laying on the surface, a better glue line results.

For the best results both surfaces of the joint should be glued. Use good quality brushes. Surfaces once glued should not be exposed to the air for any length of time. Do not over cramp; it's possible to starve a joint this way

A minimum of twenty minutes closed assembly time should be allowed before the application of pressure.

Just bring the surfaces firmly into contact.

This will enable the glue to penetrate the surface fibres of the timber and avoid excessive squeeze out.

## **STORAGE**

The powder resin should be stored in the original bags/containers in a cool place protected from heat. When stored at higher temperature, the storage stability will impair considerably.

Care should be taken that powder does not absorb moisture and water. The bags, which have been opened, should be carefully closed before storage. When stored in original bags at 20C, shelf life would be over six months. Towards end of its storage life, viscosity would increase and gel time would decrease.

Do not allow to reach 30C. Cascamite exposed to heat will require a lot more water to activate.

Store Cascamite WBP in a cool dry place with the container tightly closed. Storage life at 25C More than 6 months

Urea Formaldehyde resin (Cascamite) is a hygroscopic material.

Because of their affinity for atmospheric moisture, hygroscopic materials require storage in sealed containers. (Plaster and cement are hygroscopic).

Once the container is opened care should be taken to ensure that the contents has minimum contact with the air. Powder should be removed quickly and the container resealed before continuing with bonding.

If these materials are stored in damp conditions, the container/sack is left open or if the containers are subject to large temperature variations the powder will partially react and although the product looks the same it will not work as an adhesive.

Semi activated adhesive will not mix properly and will separate out when mixing is attempted.

Stored in the correct conditions with minimum air exposure the product will last for long periods.

Heat and moisture will cause the glue powder to become solid or insoluble. Claims for loss due to neglect of this warning cannot be accepted.

## **CLEANING OF CONTAINERS AND TOOLS**

Wash down equipment with clean cold water before the glue sets. After the glue has set it becomes hard and difficult to remove. In particular, glue should not be allowed to harden on brushes or rollers.

**WARNING:** The fully cured adhesive can only be removed by mechanical means (sawing, sanding etc).

## **HEALTH & SAFETY**

Synthetic glues may cause dermatitis in some people. As a precaution, any glue spilt on the hands should be removed immediately with soap and water before it sets. Avoid the formation or spread of dust in the air. Wear suitable protective clothing, gloves and eye/face protection. Ensure good ventilation. Keep out of reach of children. Contact with eyes - wash immediately with warm water. Remove excess from tools and mixing vessels before washing in warm soapy water. Do not empty into drains or watercourses.

Further information may be obtained from:

Polyvine Limited, Vine House, Cheddar Business Park, Wedmore Road, Cheddar, BS27 3EB

Tel 01934 740305 • [www.polyvine.com](http://www.polyvine.com) • email [info@polyvine.co.uk](mailto:info@polyvine.co.uk)

The information supplied herein is accurate to the best of our knowledge. Since conditions and methods are beyond our control, no warranty is expressed or implied. You are advised to assess the suitability of the product on a test area before application

Date of issue: January 2019

Further information may be obtained from:

Polyvine Limited, Vine House, Cheddar Business Park, Wedmore Road, Cheddar, BS27 3EB

Tel 01934 740305 • [www.polyvine.com](http://www.polyvine.com) • email [info@polyvine.co.uk](mailto:info@polyvine.co.uk)